

TILE APPLICATIONS	RESIDENTIAL	LIGHT COMMERCIAL	COMMERCIAL
Floors		100	
Walls/Backsplashes			
Countertops			
Exterior			

TECHNICAL INFORMATION

TEST	RESULTS	ANSI STANDARDS	ASTM #
Abrasion Resistance (PEI)	Class IV/III	Class 0-V	ASTM C1027
Chemical Resistance	Resistant	As Reported	ASTM C650
Bonding Strength (psi)	>50 psi	≥50 psi	ASTM C482
Dynamic Coefficient of Friction (DCOF)*	>0.42	As Reported	ANSI A 137.1-2012
Scratch Hardness	6.5	MOHS 1-10	MOHS Scale
Water Absorption	<0.50%	≤0.50%	ASTM C373
Breaking Strength	>450 lbf.	>250 lbf.	ASTM C648
Frost Resistance	Resistant	As Reported	ASTM C1026
Stain Resistance	Resistant	As Reported	ASTM C1378
Crazing Resistance	Resistant	As Reported	ASTM C424
Thermal Shock	Resistant	As Reported	ASTM C484
Recycled Content (Pre-Consumer)	12.50%	N/A	N/A
Recycled Content (Post-Consumer)	23.70%	N/A	N/A





BLACK FOREST

Glazed Porcelain Rectified Floor Tile

Interceramic® CRAFTED FOR LIFE





Suitable Rooms





























Blauen Black

PELIV

PELIII

SIZES

Kandel Brown

11½"x47" R 7½"x47" R Up to 36 Faces Up to 54 Faces



Variation Rating: HIGH High shade and texture variation with in each carton





