

USAGE INFORMATION

ī	TILE APPLICATIONS	RESIDENTIAL	LIGHT COMMERCIAL	COMMERCIAL
ı	Floors		TATES - 214 TELESTA	
L	Walls/Backsplashes			
	Countertops	•		
	Exterior			
	PLEASE NOTE: Not recommended for ramps	or floor areas exposed to water or h	eavy grease accumulation.	

TECHNICAL INFORMATION

TEST	RESULTS	ANSI STANDARDS	ASTM #
Abrasion Resistance (PEI)	Class IV/III	Class 0-V	ASTM C1027
Chemical Resistance	Resistant	As Reported	ASTM C650
Bonding Strength (psi)	>50 psi	≥50 psi	ASTM C482
Dynamic Coefficient of Friction (DCOF)*	>0.42	As Reported	ANSI A 137.1-2012
Scratch Hardness	7.5	MOHS 1-10	MOHS Scale
Water Absorption	<0.50%	≤0.50%	ASTM C373
Breaking Strength	>450 lbf.	>250 lbf.	ASTM C648
Frost Resistance	Resistant	As Reported	ASTM C1026
Stain Resistance	Resistant	As Reported	ASTM C1378
Crazing Resistance	Resistant	As Reported	ASTM C424
Thermal Shock	Resistant	As Reported	ASTM C484
Recycled Content (Pre-Consumer)	12.50%	N/A	N/A
Recycled Content (Post-Consumer)	23.70%	N/A	N/A

*It is important to note that Dynamic Coefficient of Friction results can vary after installation due to the presence of foreign materials, such as water, oil and other material the length of the human stride at the time of slip; type of floor finish and condition of shoe sole.





INDUSTRY

Glazed Porcelain Floor Til

Interceramic®





Suitable Rooms



























PEI III

















PEI IV

PEI IV























TRIM (Available in all colors)







